

PRODUCT TECHNICAL DATA SHEET

SOLID | SOLID STANDARD



High pressure decorative laminates (HPL), having thickness 2 mm or greater, according to EN 438-4:2005 or EN 438-8:2005, consisting of a surface of decorative paper(s), on one or both sides, impregnated with aminoplastic resins and a core made of layers of kraft paper impregnated with phenolic thermosetting resins. All the layers are bonded together with simultaneous application of heat (approximately 150°C) and high specific pressure (> 7 MPa) to obtain a homogeneous non-porous material with increased density. When these laminates are self-supporting they are ready for installation. They are available in the standard CGS and ATS and in the flame retardant CGF and ATF types.

EN 438-4 EN 438-8 Standard	Decor	Plain colours	Printed decors	Iridescent colours
	EN 438 classification	CGS/CGF	CGS/CGF	ACS/ATF
Standard	EN 438-4	EN 438-4	EN 438-4	EN 438-8

PROPERTIES	TEST METHOD	PROPERTY OR ATTRIBUTE	UNIT	VALUES
------------	-------------	-----------------------	------	--------

SURFACE QUALITY

Surface quality	EN 438-2.4	Spots, dirt and similar surface defects Fibres, hairs and scratches	mm <sup>2</sup> /m <sup>2</sup> mm/m	≤ 1 ≤ 10
-----------------	------------	--	---	-------------

DIMENSIONAL TOLERANCES

Dimensional tolerances	EN 438-2.5	Thickness tolerance	mm	2.0 ≤ t < 3.0: ± 0.20
			mm	3.0 ≤ t < 5.0: ± 0.30
			mm	5.0 ≤ t < 8.0: ± 0.40
			mm	8.0 ≤ t < 12.0: ± 0.50
			mm	12.0 ≤ t < 16.0: ± 0.60
			mm	16.0 ≤ t < 20.0: ± 0.70
			mm	20.0 ≤ t < 25.0: ± 0.80
	mm	25.0 ≤ t: ± 1.40		
	EN 438-2.6	Length and width	mm	+ 10 / - 0
	EN 438-2.7	Straightness of edges	mm/m	≤ 1.5
EN 438-2.8	Squareness	mm/m	≤ 1.5	
EN 438-2.9	Flatness (measured on full-size sheet).	mm/m	2.0 t < 6.0: ≤ 8	
		mm/m	6.0 ≤ t < 10.0: ≤ 5	
		mm/m	10.0 ≤ t: ≤ 3	

GENERAL PROPERTIES

Resistance to surface wear	EN 438-2.10	Initial Point Wear value	Revolutions Revolutions	≥ 150 ≥ 350	≥ 100 ≥ 200	N/A N/A
Resistance to immersion in boiling water	EN 438-2.12	Mass increase - 2 ≤ t < 5 mm	%			CGS e ATS ≤ 5.0 - CGF e ATF ≤ 7.0
		Mass increase - 5 ≤ t 1 mm	%			CGS e ATS ≤ 2.0 - CGF e ATF ≤ 3.0
		Thickness increase - 2 ≤ t < 5 mm	%			CGS e ATS ≤ 6.0 - CGF e ATF ≤ 9.0
		Thickness increase - 5 ≤ t 1 mm	%			CGS e ATS ≤ 2.0 - CGF e ATF ≤ 6.0
		Appearance - Gloss Finish	Rating			≥ 3
Resistance to water vapour	EN 438-2.14	Appearance - Gloss Finish	Rating			≥ 3
		Appearance - Other finish	Rating			≥ 4
Resistance to dry heat (180°C/20")	EN 438-2.16	Appearance - Gloss Finish	Rating			≥ 3
		Appearance - Other finish	Rating			≥ 4
Resistance to wet heat (100")	EN 12721:1997	Appearance - Gloss Finish	Rating			≥ 3
		Appearance - Other finish	Rating			≥ 4
Dimensional stability at elevated temperatures	EN 438-2.17	Cumulative dimensional change - 2 ≤ t < 5 mm	Longitudinal %			≤ 0.40
		Cumulative dimensional change - 5 ≤ t 1 mm	Longitudinal %			≤ 0.30
		Cumulative dimensional change - 2 ≤ t < 5 mm	Transversal %			≤ 0.80
		Cumulative dimensional change - 5 ≤ t 1 mm	Transversal %			≤ 0.60
Resistance to impact with large diameter ball	EN 438-2.21	Indentation diameter - 2 ≤ t < 6 mm with 1.4 m drop height	mm			h 1400 / d ≤ 10
		Indentation diameter - 6 ≤ t 1 mm with 1.8 m drop height	mm			h 1800 / d ≤ 10 h 800 / d ≤ 12 h 800 / d ≤ 12
Resistance to crazing	EN 438-2.24	Appearance	Rating			≥ 4
Resistance to scratching	EN 438-2.25	Appearance - Smooth Finishes	Rating			≥ 2
		Appearance - Textured Finishes	Rating			≥ 3 ≥ 2
Resistance to staining	EN 438-2.26	Appearance - Group 1 & 2	Rating			≥ 5
		Appearance - Group 3	Rating			≥ 4
Light fastness (Xenon-arc)	EN 438-2.27	Contrast	Grey scale rating			≥ 4
Resistance to cigarette burns	EN 438-2.30	Appearance	Rating			≥ 3 N/A
Flexural modulus	EN ISO 178	Stress	Mpa			≥ 9000
Flexural strength	EN ISO 178	Stress	Mpa			≥ 80
Density	EN ISO 1183	Density	g/cm <sup>3</sup>			≥ 1.35

FIRE PERFORMANCES

Reaction to fire / CGS and ACS types	EN 13501	Classification - 2 mm ≤ t < 6 mm	Classification		D-s1,d0 (metal frame)
		Classification - t ≥ 6 mm	Classification		C-s1,d0 (metal frame)
		Classification - t ≥ 2.5 mm	Classification		D-s2,d0 (wood frame)
Reaction to fire / CGF and ACF types	EN 13501	Classification - t ≥ 2.5 mm	Classification		B-s1,d0 (metal frame)
		Classification - 3 mm ≤ t < 6 mm	Classification		C-s2,d0 (metal frame and wood frame)
		Classification - t ≥ 6 mm	Classification		B-s1,d0 (metal frame and wood frame)

OTHER PROPERTIES

Thermal resistance / conductivity	EN 12664	Thermal resistance / conductivity	W/mK		0.2 to 0.5
Formaldehyde emission	EN 717-1	Chamber method	mg/m <sup>3</sup> ppm		0.020 - 0.035 0.015 - 0.030
	EN 717-2	Gas analysis	mg/(m <sup>2</sup> x h)		0.2 - 0.4
	EN 13986	Classification	Rating		E1
Volatile Organic Chemical Emissions	GGPS.002 Greenguard Children & School Standard according to US California Dept. of Health Services (CA section 01350)	Individual VOCs	TLV / CA chronic REL		≤ 1/100 / ≤ 1/2
		Formaldehyde	ppm / ppb		0.0135 / 13.5
		TVOC	mg/m <sup>3</sup>		≤ 0.22
		Total Aldehydes	ppm / ppb		0.043 / 4.3
		Total Phthalates	mg/m <sup>3</sup>		≤ 0.01
EN 1186-3	3% acetic acid 24h at 40°C				< 10
EN 1186-3	50% ethanol 24h at 40°C				< 10
EN 1186-14	95% ethanol 24h at 40°C				< 10
EN 1186-14	isooctane 24h at 40°C				< 10
EN 13130-23	3% acetic acid 24h at 40°C				< 15
Evaluation of micro-organisms action	EN ISO 846	Microbial growth - Smooth finish	Rating		0 - no microbial growth
		Microbial growth - Textured finish	Rating		1 - slight and slow microbial growth

Note to digital printing decoratives

For the chemical-physical characteristics of digital printing, the laminates with these decoratives may present a limitation in the applications, such as the repeated and intense contact with water or vapour. Customers are asked to contact the Customer Service Arpa Industriale to evaluate the best solution.

Disclaimer

The Product Technical Sheets provide all the technical information relevant to the performance of the product as tested by Arpa Industriale or certified testing agencies. Arpa Industriale maintains the right to change and alter the product composition and production process and thereby the performance characteristics of the product at all times, as reported to the Arpa Industriale website. Customers and end-users of the product are requested to check for the latest technical information regarding the products performance on the website of Arpa Industriale before application. In any case, Arpa Industriale, in every contractual relationship, will refer only to the technical information published on its website. Arpa Industriale will not assume any liability if the end-user or customer refer to any other technical information of the products.